


Clipperlon 2100

Modified PTFE



Description

PTFE gaskets offer outstanding chemical stability, which makes them ideally suited for use in the chemical industry. In addition, a majority of PTFE products are FDA approved which makes them perfect for use in the food and pharmaceutical industries.

The Clipperlon 2100 is a very dense material with low compressibility, high recovery and low creep properties. The gasket has a fawn colour and is produced with Modified PTFE containing solid silica beads as a filler.

Sealing Characteristics

- Excellent sealability;
- Outstanding chemical resistance;
- Significant reduced creep (non-cold flow);
- Low leak rate;
- Good electrical insulation properties;
- Non ageing.

Application

A general purpose gasket material for sealing applications across the whole pH-range.

Applications can be found in chemical food and beverage and general industry.

Chemical compatibility, pressure and temperature

Particularly suitable for use with strong acids (except hydrofluoric acid) and alkalis. Other applications include solvents, fuels, water, steam and chlorine. A chemical resistance list available upon request.

Pressure up to 85 bar

Temperature from – 240 °C up to 260 °C

Delivery options

Flange gaskets and sheets are available in thickness of 0,5/0,8/1/1,6/2/3/4,8/6,4mm. Standard gaskets can be supplied in accordance with ASME B16.21, EN12560-1 as well as EN1514-1. Non-standard or special gaskets can be manufactured according to customer drawings, or by given sizes or E-drawings.

Approvals and Certificates

TA-Luft

FDA 21 CFR 177.1550

EC1935 (10/2011)

Table 1: Technical data

	Norm	Value	Unit
Minimal initial stress	DIN 28090-1	20	MPa
Maximum initial stress	DIN 28090-1	160	MPa
Minimum temperature		-210	°C
Maximum temperature		260	°C
Compression	ASTM F36	7-10	%
Recovery	ASTM F36	40	%
Maximum pressure**		85	bar
Density		2,2	g/cm ³
Gas Permeability	DIN 3535/6	0,01	cm ³ /min
Specific Leak Rate	DIN28090 - 2	0,001	mg/(s*m)
M-Factor		3,5	
Y-Factor		2450	PSI
Creep relaxation	ASTM F 38	23	%

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

For more information, quotations or orders: Phone +31 72 514 18 44 or E-mail seals@eriks.nl