



NBR 60 compound 366674

Characteristics

- Colour: Blue
- Temp. resistance low: -20 °C
- Temp. resistance high: 100 °C
- Hardness tolerance: -5/+5

Approval & Compliancy details

For Food & Beverage compliances, see Declaration of Compliance for typical application of the compound.

- Bisphenol A free
- EC1935:2004
- Phtalates free
- REACH
- RoHS
- TSCA



Products

- Custom parts (moulded)
- Flat shapes (punched or cut)

Table: Physical Properties

Property	Value	Unit
Hardness Shore A - Slab	60	
Hardness - Test standard	ISO7619	
Compression set - Slab	30	%
Compression set - Duration @ temperature	24 hours at 70°C	
Compression set Test standard	ISO815	
Elongation at break	400	%
Elongation at break - Test standard	ISO37	
Tensile strength	9	MPa
Tensile strength - Test standard	ISO37	