

## EPDM White 131302



**Material**  
EPDM

**Color**  
Wit

**Density (gr/cm3)**  
1,29

**Hardness (Shore A)**  
60 +/-5

**Pressure max. (bar)**  
10

**Temperature limits (°C)**  
-30°C to max +120°C

**Application**  
Resistant to weathering and UV resistant.  
Suitable for acids and alkalines.

**Approvals and certificates**

- EC 1935/2004
- FDA

**Table 1: Technical data\***

Gasket factor	Norm	Value	Unit
Maximal surface pressure $\sigma_{v_0}$	DIN 29090	10	MPa
Minimum temperature		-35	°C
Maximum temperature		+120	°C
Hardness	ISO 7619	60	Shore A
Elongation at break	DIN 35304	450	%
Tensile strength	DIN 35304	>9	MPa
Density		1,29	g/cm <sup>3</sup>

\* depending on temperature and construction

**Table 2: Supply programme\***

Thickness (mm)	Inlays	Width (mm)	length (m)	Partnumber
2	-	1400	20	11268709
3	-	1400	10	11247893
4	-	1400	10	11268710
5	-	1400	10	11247894
6	-	1400	1	12224668
8	-	1400	5	11118644
10	-	1400	5	12522030

\* Gaskets can be produced according to industry standards or according to drawings.

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.

**For more information, quotations or orders:**

**The Netherlands :** +31 88 855 80 44 of [gaskets@eriks.nl](mailto:gaskets@eriks.nl)

**Belgium : Dutch** +32 3 210 91 10 of [flangegaskets@eriks.be](mailto:flangegaskets@eriks.be)

**Francophone** +32 71 91 50 64 of [flangegaskets@eriks.be](mailto:flangegaskets@eriks.be)

page 1/1