

Leader Fybar PT 20

Rubberbonded Fiber Jointing Sheets

DESCRIPTION

Fibre PT20 consists of mineral and aramid fiber, NBR bound. Fiber gasket for low temperature. Suitable for pressure testing.

APPLICATION

utilities and non-aggressive media such as water, air, oil, greases and fuels

DELIVERY OPTIONS

Flange gaskets and sheets are available in thickness of

0,5mm, 1mm, 1,5mm, 2mm and 3mm. Other thicknesses available on request.. Standard gaskets can be supplied in accordance with ASME B16.21, EN12560-1 as well as EN1514-1. Non-standard or special gaskets can be manufactured according to customer drawings, or by given sizes or Edrawing.

TEMPERATURE

Temperature from -30 °C up to +130 °C

TECHNICAL DATA

max Temperature [°C]	130
min Temperature [°C]	-30
max Pressure [bar]	40
density [g/cm ³]	1,6 - 2
Minimum initial stress [DIN E 2505 part 2] [N/mm ²]	20
Maximum initial stress [DIN E 2505 part 2] [N/mm ²]	120
M-Value	2.5
Y- Value [psi]	2175
ASTM F36 Recovery [% min]	45
Gasket required flange roughness [Ra micron]	3,2-6,3
Gasket required flange roughness [RMS]	125-250
max Seating stress [Q _{smax} bei RT EN13555] [n/mm ²]	130
Tensile Strength (quer) DIN 52910 [N/mm]	7.5

LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Pšurnovická cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895