

Leader Fybar PT 50

Rubberbonded Fiber Jointing Sheets



DESCRIPTION

Fybar PT50 consists of aramid fiber, NBR bound universally applicable, excellent value/quality ratio. Widely applicable for non-aggressive media, such as air, (potable) water, oils, greases and fuels, weak acids and alkalines.

APPLICATION

Widely applicable for non-aggressive media such as air, (potable) water, oil, grease and fuel, weak acids and alkalines

CHEMICAL COMPATIBILITY

DELIVERY OPTIONS

Flange gaskets and sheets are available in thickness of 0,5mm, 1mm, 1,5mm, 2mm and 3mm. Other thicknesses available on request.. Standard gaskets can be supplied in accordance with ASME B16.21, EN12560-1 as well as EN1514-1. Non-standard or special gaskets can be manufactured according to customer drawings, or by given sizes or Edrawing.

TEMPERATURE

Temperature from -30 °C up to +200 °C

- BS7531 Grade Y
- GL
- UBA ELL 'KTW'
- HTB
- DVGW
- W270
- TA-Luft

APPROVALS & CERTIFICATES

TECHNICAL DATA

max Temperature [°C]	200
min Temperature [°C]	-30
max Pressure [bar]	85
density [g/cm ³]	1.7
Minimum initial stress [DIN E 2505 part 2] [N/mm ²]	17
Maximum initial stress [DIN E 2505 part 2] [N/mm ²]	180
M-Value	2.5
Y- Value [psi]	3900
min Seating stress [Qmin(L 0,01), mg/(s*m)] at RT 40 bar [N/mm ²]	30
ASTM F36 Recovery [% min]	55
Gasket required flange roughness [Ra micron]	3,2-6,3
Gasket required flange roughness [RMS]	125-250
max Seating stress [Qsmax bei RT EN13555] [n/mm ²]	180
Relaxation PQR (30 MPA 150°C) [%]	0.8
Residual seating stress , [QA=40 MPA, Qmin(L 0,01), mg/(s*m)] bei RT 40 bar [N/mm ²]	10
Tensile Strength (quer) DIN 52910 [N/mm]	6

LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Purnovicka cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895