

## tesa® 4959

### Double-sided non-woven tape

tesa® 4959 is a double-sided mounting and splicing tape equipped with a non-woven backing and coated with an acrylic adhesive of high tack and good shear strength. It is UV and ageing resistant and largely resistant to plasticizers.

### Main Application

- Mounting of signs, covers and nameplates
- Mounting of door linings in the car industry
- Mounting of plastic bags, dispatch bags, continuous stationery, posters etc.
- Splicing of paper and film webs

### Technical Data

▪ Backing material	non-woven	▪ Tensile strength	8 N/cm
▪ Color	translucent	▪ Type of liner	glassine
▪ Total thickness	100 µm	▪ Colour of liner	brown
▪ Type of adhesive	tackified acrylic	▪ Thickness of liner	71 µm
▪ Elongation at break	3 %		

### Adhesion to

▪ Steel (initial)	8.0 N/cm	▪ Steel (after 14 days)	8.5 N/cm
▪ ABS (initial)	7.5 N/cm	▪ ABS (after 14 days)	9.0 N/cm
▪ Aluminium (initial)	7.5 N/cm	▪ Aluminium (after 14 days)	8.0 N/cm
▪ PC (initial)	9.5 N/cm	▪ PC (after 14 days)	14.0 N/cm
▪ PE (initial)	4.0 N/cm	▪ PE (after 14 days)	4.5 N/cm
▪ PET (initial)	7.0 N/cm	▪ PET (after 14 days)	7.5 N/cm
▪ PP (initial)	5.5 N/cm	▪ PP (after 14 days)	6.5 N/cm
▪ PS (initial)	8.5 N/cm	▪ PS (after 14 days)	9.0 N/cm
▪ PVC (initial)	6.5 N/cm	▪ PVC (after 14 days)	14.0 N/cm

### Properties

▪ Temperature resistance short term	200 °C	▪ Softener resistance	●●
▪ Temperature resistance long term	80 °C	▪ Static shear resistance at 23°C	●●●
▪ Tack	●●●●	▪ Static shear resistance at 40°C	●●
▪ Ageing resistance (UV)	●●●●		
▪ Humidity resistance	●●●		
▪ Resistance to chemicals	●●●		

Evaluation across relevant tesa® assortment: ●●●● very good ●●● good ●● medium ● low

For latest information on this product please visit <http://l.tesa.com/?ip=04959>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

tesa® 4959

Double-sided non-woven tape

### Additional Information

Liner variants:

PV0 brown glassine paper (71 µm)

PV6 red MOPP-film (80 µm)

PV36 double lined brown glassine paper

According to VDA278 analysis, tesa 4959 does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan).

For latest information on this product please visit <http://l.tesa.com/?ip=04959>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.